

Kiyanly Refinery (Turkmenistan)

Polypropylene L H3066-03.O

L H3066-03.O is intended for use in the production of biaxial-orientation polypropylene film and is recommended as a resin for laminating film and snack / bakery wrapper or used in the production of metallized film.

L H3066-03.O designed to provide:

- appropriate processing ability
- good optical properties
- high strength properties

Typical physical properties

No	Description of Index	Rate
1	Volume speed of fluidity (at 230°C, 2,16 kg), g/10 min	3,4
2	Density, g/cm ³	0,902
3	Tensile yield strength	32
4	Elongation at yield, %, not less than	9
5	The elasticity module at a bend, N/mm ² , not less than	1400
6	Shock durability by Izod (with a cut 23°C) kDj/m ²	50

The stated properties are measured typical product values and should not be considered as technical specifications.