

Kiyanly Refinery (Turkmenistan)

Polypropylene L R7175-35.P

L R7175-35.P is designed for use in injection molding processes and recommended for use in packaging and consumer household utensils

L R7175-35.P designed to provide:

- weak taste and smell
- good development skills

Typical physical properties

No	Description of Index	Rate
1	Volume speed of fluidity (at 230°C, 2,16 kg), g/10 min	35
2	Density, g/cm ³	0,902
3	Strength at a stretching in a fluidity limit, N/mm ² , not less than	28
4	Elongation at yield, %, not less than	8
5	The elasticity module at a bend, N/mm ² , not less than	1100
6	Shock durability by Izod (with a cut 23°C) kDj/m ²	38

The stated properties are measured typical product values and should not be considered as technical specifications.